

Your search

Product series:

- Wax dispersions

Product list

Water-based wax dispersions	Drop point °C	Solid content %	Particle size 98 % x µm	PDF
DEUREX A 2008 W Water-based wax dispersion based on Ethylene-Bis-Stearamide wax	142-151	17-20	8	TDS MDS
DEUREX E 0908 W Water-based wax dispersion based on PE wax	110-120	44-46	8	TDS MDS
DEUREX EO 4508 W Water-based wax dispersion based on oxidized HDPE wax	138	49-51	8	TDS MDS
DEUREX F 6408 W Water-based wax dispersion based on PTFE coated wax	110-120	44-46	8	TDS MDS
DEUREX H 7308 W Water based hybrid wax dispersion, Carnauba wax and hard paraffin	85-95	44-46	8	TDS MDS
DEUREX H 9108 W Water based hybrid wax dispersion, Fischer-Tropsch wax and polyethylene wax	110-120	44-46	8	TDS MDS
DEUREX H 9208 W Water-based wax dispersion based on the hybrid wax H 92	130-140	33-36	8	TDS MDS
DEUREX P 3608 W Water-based wax dispersion based on polypropylene wax	150-170	44-46	8	TDS MDS
DEUREX P 3808 W Water-based wax dispersion based on polypropylene wax	145-155	34-36	8	TDS MDS
DEUREX S 3208 W Water-based wax dispersion based on a Silica coated wax	110-120	20-23	8	TDS MDS

Product list

Water-based wax dispersions	Drop point °C	Solid content %	Particle size 98 % x µm	PDF
DEUREX T 1908 W Water-based wax dispersion based on Fischer-Tropsch wax	83-91	44-46	8	TDS MDS
DEUREX T 3908 W Water-based wax dispersion based on Fischer-Tropsch wax	110-120	44-46	8	TDS MDS
DEUREX X 2008 W Water-based wax dispersion based on vegetable EBS wax	142-151	17-20	8	TDS MDS
DEUREX X 5505 W Water-based wax dispersion based on Carnauba wax	81-90	39-41	5	TDS MDS

Oil-based wax dispersions	Drop point °C	Solid content %	Particle size 98 % x µm	PDF
DEUREX C 0112 O Oil-based wax dispersion of EDTA-Na2	-	34-36	12	TDS MDS
DEUREX F 6012 O (35 %) Oil-based dispersion based on PTFE	-	34-36	12	TDS
DEUREX F 6412 O Oil-based wax dispersion based on PTFE coated wax	110-120	34-36	12	TDS MDS
DEUREX T 3912 O Oil-based wax dispersion based on Fischer-Tropsch wax	110-120	34-36	12	TDS MDS